



Technical data sheet

Instant adhesive

MD GLUE BS.406

06.10.2016

low viscosity

NSF Registration No. 150268 Category Code: P1

Base	Ethyl Cyanacrylat
Color	transparent
Viscosity 20°C	3-10 mPa.s
Density	1,05 g/cm ³
Setting time aluminium	5-10 seconds
Setting rubber	2-5 seconds
Final cure	24 hours
Max. gap filling	0,05 mm
Temperature resistance	-50°C to +80°C
Thermal conductivity ASTM C 177	0,1
Tensile shear strength steel DIN 53283	22 N/mm ²
Shelf life at 5°C to 8°C	12 months

REACH registered

Not included in this product:

Amines, benzene, benzoyl, biocides, bisphenol, DEHP, peanut oil, halogen, latex, Nanoparticles, persistent, perfluorierte surfactants, PFOA, PFOX, phthalates, silicone

Description to use:

The parts to be bonded must be clean, oil- and greasefree. Give MD GLUE thinly on one side and pressing parts together. To accelerate the curing, you can use MD ACTIVATOR NO. 9 No.9. To accelerate the curing of materials such as PP, PE, Teflon or silicone you can use our MD PRIMER NO. 7.

The values are average values. They serve merely for your information, but assume no warranty.

Bergheimer Str. 15 | D-53909 Zülpich | Tel. 02252/94150 | info@marston-domsel.de
www.marston-domsel.de

The information in this product has been compiled to the best of our knowledge and is intended purely for information purposes. No claims can be inferred therefrom. Before use, thorough experiments should be carried out. Our brochure represents a basis. Responsibility for possible measures to protect property and persons lies with the user. Safety data sheets on the required standard are available for all products on request.



Technical data sheet

Instant adhesive

Material combinations	MD GLUE BS.406 Instant adhesive
metal	++
plastic*	++
rubber	++
EPDM-Elastomeric	++
wood	
glas/ceramic	+
leather	
comment	rapidly bond capillarity
+ suitable ++ ideal	
Storage	cool, dry, dark, optimum temperature 6°C to 8°C
RoHS conform	
Packaging	Item number
25 bottles á 10 g	MGL.BS.F10
12 bottles à 20 g / display	MGL.BS.F20
12 bottles à 50 g / display	MGL.BS.F50
1 bottle á 500 g	MGL.BS.F500
1 container á 20 kg	MGL.BS.K20
Other packaging on request	

Bergheimer Str. 15 | D-53909 Zülpich | Tel. 02252/94150 | info@marston-domsel.de
www.marston-domsel.de

The information in this product has been compiled to the best of our knowledge and is intended purely for information purposes. No claims can be inferred therefrom. Before use, thorough experiments should be carried out. Our brochure represents a basis. Responsibility for possible measures to protect property and persons lies with the user. Safety data sheets on the required standard are available for all products on request.